Product Parameters:	
Pile Material:	Acrylic; Polyester; Shaggy; Microfiber
Pile Weight:	700g/sqm; 800g/sqm; 900g/sqm 1000g/sqm; 1200g/sqm;1600g/sqm; etc.,
Backing:	Cloth; TPR; Non-woven
Size:	3’x4’; 3’x5’;4’x6’;4’x8’,6’x8’;6’x10’ custom size also available
Certificate:	REACH&Oeko-TEX Standard 100
Use For:	Living Room, Floor, Decoration

Area Rug:

Best Quality, Exquisite Priting, Soft Feeling

Pattern: High Definition Area Rug

High Definition printing, words and design could be printed as requested

Acrylic or Polyester surface, high density can feel comfortable walking on it

Pattern: Loop Pile Area Rug

Loop Polyester can print complicate design

Loop Pile surface more durable and easy cleaning

- Soft in touch, super water absorption, quick-drying excellent cleaning ability
- Suitable for bedroom,sitting room,washroom,sofa
- Many choice for colors and designs

High Definition Style:

Loop Pile Style:

Area Rug:

Best Quality, Exquisite Priting, Soft Feeling

Pattern: Shaggy Area Rug

Polyester Shaggy Surface, soft touching for its high thickness

Super water absorption

Pattern: Microfiber Area Rug

Microfiber surface, high density skin-friendly feeling

Anti-slip and water absorption

Exhibitions:

DOMOTEX Germany

DOMOTEX Shanghai

Canton Fair

China Sourcing Fair(HK)

Packaing:



Certificate:

ITTC

No.399, Gongwen Road, Fengxian District Shanghai, China 201413
Tel: (86-21) 3753 4800 Fax: (86-21) 3753 4819

Determination Of Formaldehyde (Refer To IOS-TM-0007; AA-300792-4, IOS-PRG-0032; AA-707377-2, ISO 14184-1: 2011)

	Formaldehyde content (mg/ kg)	IKEA Limit
Mean value	Not detectable	/

No.	1	2
Individual value	Not detectable	Not detectable

- *The standard curve is performed once a month.*
- *The concentration of formaldehyde stock solution is certified by Hach-Lange.*

Remark:

- *Value below 16 ppm is reported as 'Not detectable'.*

Determination Of pH Of Aqueous Extract (Refer To IOS-TM-0007; AA-300792-4, IOS-PRG-0032; AA-707377-2, ISO 3071: 2005, extract by distilled water)

pH Value	IKEA Limit
6.5	/

Temperature of extracting solution, ℃	*24*
pH of distilled water	*6.18*

End of Report

Test Report No.:26706010

Page 2 of 2

Formaldehyde content (mg/
Not detectable
1
Not detectable
once a month

CONFIDENCE IN TEXTILES
Tested for harmful substances
according to Oeko-Tex® Standard 100
ZHGO 069166 TESTEX

SYSTEM CERTIFICATION
ISO 14001:2004
SGS